

TECHNICAL DETAILS**COVERAGE RATE*****SMOOTH SUBSTRATES:**0.037 kg/sf
0.40 kg/m²**FINE GRAINED SUBSTRATES:**0.046 kg/sf
0.50 kg/m²**ROUGH SUBSTRATES:**0.074 kg/sf
0.80 kg/m²**PACKAGING**

1-kg container

COLOR

White

CATALYST CALCULATOR†**37-50°F (3-10°C)**6 scoops
60 g**50-68°F (10-20°C)**4 scoops
40 g**68-95°F (20-35°C)**2 scoops
20 g**REACTION TIMES@68°F (20°C)**

Pot Life: ≈10-15 minutes

Rainproof: ≈30 minutes

Fully Cured: ≈3 hours

FEATURES & BENEFITS

- Promotes bonding to concrete, wood, and asphalt substrates
- EZ Seal membranes are monolithic, flexible and seamless
- Ideal for access-restricted areas and difficult waterproofing conditions

* Gross yield/container is approximate. See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

† Measures amount of EZ Seal Catalyst required per 1 kg of primer. Scoop provided with catalyst measures 10 g. In most situations, 2 scoops of catalyst per kg of primer is satisfactory.

EZ SEAL WHITE COMBO PRIMER

PRODUCT USE

754-1 EZ Seal White Combo Primer is a high performance, rapid-curing primer used to promote bonding of concrete, masonry, wood, asphalt cap sheet membranes, or other recommended substrates with EZ Seal liquid-applied roofing membranes. Malarkey Roofing Products® EZ Seal System is waterproof, flexible, self-adhering, and ideal for access-restricted and difficult waterproofing conditions. EZ Seal conforms and bonds directly to the substrate, eliminates the need for caulk and pitch pans, and is virtually maintenance-free.

COMPOSITION & MATERIALS

EZ Seal White Combo Primer is a two-component, poly methyl-methacrylate (PMMA) resin primer. It is activated with Malarkey Roofing Products® EZ Seal Catalyst Powder (790-2).

APPLICATION/INSTALLATION

Before adding catalyst, pour EZ Seal White Combo Primer into a second container for batch mixing and stir. Add pre-measured catalyst, mix, and stir again. Catalyze only the amount of material you can use within 10-15 minutes. Apply to substrates prepared as specified in the EZ Seal Application Instructions. Application over the primer should take place within 12 hours. Contact Malarkey's Technical Services Department for details.

PRECAUTIONS

EZ Seal White Combo Primer is harmful by inhalation and irritating to eyes and skin. Vapors may form an explosive mixture with air so keep away from heat, flame and ignition sources. To ensure safety when handling, the user should wear appropriate PPE, including respirator in enclosed spaces. Wash thoroughly after handling. Consult SDS for complete details.

EZ Seal White Combo Primer shall be stored in its original container with adequate ventilation. When not in use, keep container closed in a cool, dry location. In case of spill, absorb with liquid-binding material, collect, and dispose of waste in accordance with federal, state and local regulations. Material and container must be disposed of as hazardous waste.

EMERGENCY INFORMATION:

For Chemical Emergency, Spill Leak, Fire Exposure or Accident
Call CHEMTREC Day or Night; in North America 800-424-9300

Substrates must be clean, dry, free of surface moisture, oil, grease, contaminants, and any other material or condition which would adversely effect bonding of EZ Seal to the substrate.

WARRANTY

Malarkey Roofing Products® offers various warranties to meet specific requirements. Contact your roofer, local distribution center or Malarkey for full details. See below for TECHNICAL ASSISTANCE contact information.

EZ Seal and other Malarkey products are available throughout North America and Pacific Rim countries.

Visit WWW.MALARKEYROOFING.COM for additional product information and availability.

Note: Malarkey Roofing Products® (Malarkey) inventory SKU number for this product: 754-1 EZ Seal White Combo Primer

TECHNICAL ASSISTANCE:

Malarkey has technical services assistance available.
Contact Malarkey for details:
Call weekdays 7:00 am to 5:00 pm Pacific Time
at 800.545.1191 or 503.283.1191.
technicalinquiries@malarkeyroofing.com

CORPORATE OFFICE:

3131 N. Columbia Blvd. Telephone: 503.283.1191
Portland, OR 97217-7472 or 800.545.1191
P.O. Box 17217 Fax: 503.289.7644
Portland, OR 97217-0217